

Stain name	Stain type	No of colours	Uses & Properties	Recommended Pre-Satin (reduces colour unevenness) / Sanding Sealer	Recommended Reducer (lessens colour intensity)	Recommended Retarder (slows drying time)	Dry to Touch (approx.)	Re-coat interval	Recommended no. of coats	Other Stains that can be cross-mixed	Can be dissolved into these finishes	Recommended Finish as a Topcoat	Sizes stocked
<b>Solar-Lux WB Dye Stain</b> B620-(colour no.)5	Metallic dye with water base liquid. High UV fade resistance	12	Transparent dye stain that penetrates into wood fibres. Colour strength can be adjusted (reduce by adding Reducer, increased by adding extra coat.	B620-0001 WB Dye Stain Base/Reducer	<b>Solar-Lux WB Reducer</b> B620-00015	Not applicable	5 Minutes	10 Minutes	To preference	None	Behlen Waterborne Urethane Finish & B610-0005, B610-0015 Wipe on Water Base Urethane	All Behlen lacquers, oils, varnishes or Urethane finishes	473ml
<b>Solar-Lux WB Wiping Stain</b> B645-(colour no.)5	Semi-transparent pigment based wiping stain	11	Opaque stain that highlights grain in wood. When used over <b>Solar-Lux WB Dye Stain</b> , it produces a strikingly deep colour with an enhanced grain pattern.	B620-0001 WB Dye Stain Base/Reducer	Not applicable	Not applicable	5 Minutes	10 Minutes	1 or 2 to preference			All Behlen lacquers, shellacs, varnishes or Urethane finishes	945ml
<b>Shading &amp; Glazing Stain</b> B514-(colour no.)6	Glaze (not used as a base colour)	2	For adding tones, highlighting, decorative effects, washed effects, etc., over sealed surfaces.	Always use over a sealer or topcoat	Not applicable	Not applicable	15 minutes	Within 6 hours	Usually 1 application to preference		Not applicable	All Behlen lacquers, varnishes or Urethane finishes	473ml
<b>Furniture Powders</b> B370-	Finely ground Pigment Powders	18	To achieve permanent spot repair - applied with padding cloth using <b>French Lac Padding Finish</b> , or brush wetted with <b>2 Minute Repair Liquid</b> .	Not applicable	Not applicable	Not applicable	Depends on product into which it is dispersed	Depends on product into which it is dispersed	To preference	Not applicable	See Uses and Properties	<b>Master Top Coat, Pre-cat Lacquer, Jet Spray Clears</b> , and all Behlen lacquers, shellacs, varnishes or Urethane finishes	28g
<b>Dry Powder Aniline Stain</b> B366-	Finely ground Aniline Powders	9	Transparent dye stain that penetrates into wood fibres. Colour strength can be adjusted based on how much powder is added to <b>Behkol Solvent</b> .	Not applicable	The powder is dissolved into <b>Behkol Solvent</b> to create the stain	Not applicable	10 minutes	20 minutes	To preference	Not applicable	Waterborne Urethane Finish. Must be concentrated into solution before adding to product.	All Behlen lacquers, varnishes or Urethane finishes	56g

Always read safety sheets. Always test products on a hidden area.

© 2011 Behlen Ltd.

Stain name	Stain type	No of colours	Uses & Properties	Recommended Pre-Satin (reduces colour unevenness) / Sanding Sealer	Recommended Reducer (lessens colour intensity)	Recommended Retarder (slows drying time)	Dry to Touch (approx.)	Re-coat interval	Recommended no. of coats	Other Stains that can be cross-mixed	Can be dissolved into these finishes	Recommended Finish as a Topcoat	Sizes stocked
<b>Wiping Stain Aerosol</b> B115-	Semi-transparent pigment based wiping stain	4	Opaque stain that highlights grain in wood.	PreStain B545-8006	Not applicable	Not applicable	10 minutes	30 minutes	To preference Spray & Wipe, 1 to 2 coats	None	Not applicable	<b>Master Top Coat, Pre-cat Lacquer, Jet Spray Clears,</b> and all Behlen lacquers	369ml
<b>Shading &amp; Glazing Aerosol</b> B114-	Semi-transparent pigment based wiping stain	4	For adding tones, highlighting, decorative effects, washed effects, etc., over sealed surfaces.	Always use over a sealer or topcoat	Not applicable	Not applicable	10 minutes	45 minutes minutes & within 6 hours	Spray & Wipe, 1 to 2 coats	Not applicable	Not applicable	<b>Master Top Coat, Pre-cat Lacquer, Jet Spray Clears,</b> and all Behlen lacquers	369ml
<b>Master Toner Aerosol</b> B103-	Dyes combined with Nitro-cellulose lacquer Aerosol	3	For shading or blending spot repairs. Will change shade of wood without loss of clarity.	Not applicable	Not applicable	Not applicable	10 minutes	30 minutes	To preference	Not applicable	Not applicable	<b>Master Top Coat, Pre-cat Lacquer, Jet Spray Clears,</b> and all Behlen lacquers	369ml
<b>Jet Spray Lacquer Toner Aerosols</b> B101-	Pigments dissolved into Nitro-cellulose lacquer Aerosol	20	For spot repairs to pieces that were toned with a pigment by the manufacturer, or toning when finishing small objects.	Not applicable	Not applicable	Not applicable	10 minutes	30 minutes	To preference	Not applicable	Not applicable	<b>Master Top Coat, Pre-cat Lacquer, Jet Spray Clears,</b> and all Behlen lacquers	369ml